Numerical and Experimental Analysis of Surface Roughness during the Milling Operation of Titanium Alloy Ti6Al4V

Ilesanmi Afolabi Daniyan, Isaac Tlhabadira, Khumbulani Mpofu, and Rumbidzai Muvunzi Department of Industrial Engineering, Tshwane University of Technology, Pretoria 0001, South Africa Email: afolabiilesanmi@yahoo.com, itlhabadira@tut.ac.za, mpofuk@tut.ac.za, rumbimuvunzi@gmail.com

Abstract—Titanium alloy (Ti-6Al-4V) has many industrial applications due to its excellent mechanical properties. However, its low thermal conductivity often results in surface and dimensional inaccuracies during machining operations. In this study, an experimental investigation was done to characterise the influence of milling parameters on the roughness of Ti-6Al-4V. The surface numerical experimentation involves the use of the Response Surface Methodology (RSM) with three factors namely: the speed, feed and depth of cut. The physical experiments were carried out using a DMU80monoBLOCK Deckel Maho 5-axis CNC milling machine and carbide-cutting ล insert (RCKT1204MO-PM S40T). The comparative analysis of the results obtained indicate that the milling parameters and cutting conditions significantly influenced the surface finish of the titanium alloy. The results obtained from the physical experiments indicate an increase in the magnitude of the surface roughness when the cutting parameters exceed their optimal values. The machining parameters which resulted in the least surface roughness (Ra: 0.035 µm, Rz: 1.12 µm and Rq: 0.277 µm) under the air cooling condition were: cutting speed (265 m/min), feed per tooth (0.05 mm) and depth of cut (0.5 mm). Information on the effect of machining parameters on surface roughness will assist manufacturers in selecting the most feasible combination of the process parameters for producing titanium alloy (Ti-6Al-4V) parts with improved surface quality.

Index Terms— process parameters, RSM, titanium alloy, surface roughness

I. INTRODUCTION

The surface finish of a work piece is a measure of its surface quality and dimensional accuracy. The parameters used to machine a work piece may influence its mechanical properties and its ability to meet the required service and functional requirements. Hence, it is important to determine the effect of machining parameters on surface finish to avoid costly and time consuming rework. The topography and the surface layer characteristics of a work piece are some of the factors which influences its surface finish. The topography of a work piece surface examines the surface finish and roughness. The surface layer characteristics determine the properties of the surface layer in respect to the required functional requirements.

Nomenclature						
T _d	Tool diameter (mm)					
F_l	Flute length (mm)					
F_n	Number of flute (mm)					
L	Overall length (mm)					
f_t	Feed per tooth (mm),					
R	Radius of cutter (mm),					
β	Helix angle (deg.)					
α1	Axial rake angle (deg.)					
α_2	Radial rake angle (deg.)					
Ra	Average surface roughness (µm)					
Rz	Maximum height of profile (µm)					
Rq	RMS of surface profile (µm)					
y_i	Ordinate of the profile					
1						

There are several factors which affect the surface finish of a material during machining operations. These include: development of residual stresses, recrystallization, machining error, cutting tool geometry, plastic deformation, change in micro structure, finishing operations, lack of process control and uncontrolled cutting parameters amongst others [1-3].

Furthermore, machining at a high temperature can provoke chemical reactions between the cutting tool and the work piece. This results in geometrical inaccuracies, cracks or distortion [4-6]. In addition, the surface finish of a material also depends on the degree of its machinability. This relates to the ease with which a material can be machined to the desired surface finish. Materials which are difficult to machine are often prone to poor surface finish when compared to other materials that are easy to machine. Some researchers have reported on the challenges in the machinability of materials such as titanium alloy to the required finish conditions. Hence, the need for tolerancing in order to determine the limits at which the surface conditions of a work piece will no longer be acceptable for the required service conditions. An improved surface

Manuscript received December 30, 2020; revised March 15, 2021. corresponding author: afolabiilesanmi@yahoo.com

finish can be obtained by controlling the temperature and residual stresses that promote distortion optimization of the process parameters during the cutting operations, selecting the cutting tool with the appropriate orientation and using effective coolants [7-10]. There is also a need for real time diagnosis and process monitoring of the cutting operations for effective process control in order to provide real time tracking and adjustment. This helps to minimize errors and optimize the cutting performance [11-12]. In order to proffer solutions to the surface roughness as a challenge during the machining of titanium alloy, many works have been reported on the use of Design of Experiment (DoE), analytical and numerical techniques involving modelling and simulation [13-15]. For instance, Tlhabadira et al. [16] reported on the computer aided modelling and experimental validation of titanium alloy (Ti6AlV) during a milling operation. The study shows that computer aided approach validated via physical experimentations can be employed for investigating the process conditions for effective milling operation of titanium alloy. Mia et al. [17] studied the surface roughness and cutting forces using different techniques such as the Artificial Neural Network (ANN), Response Surface Methodology (RSM), and Analysis of Variance (ANOVA) in turning of Ti-6Al-4V under cryogenic jet applied flank and rake faces of the cutting tool. The study established a link between the magnitude of the cutting forces and the resulting surface roughness in the work piece. Furthermore, Ribeiro Filho [18] investigated the influence of cutting parameters on the surface quality and corrosion behaviour of Ti6Al4V in synthetic body environment (SBF) using Response Surface Method. This study revealed that the cutting parameters can significantly influence the surface finish and corrosion behaviour of titanium alloy. Similar findings on the effect of cutting parameters on surface integrity in milling Ti6Al4V were reported by Oosthuizen, et al. [19]. In addition, Kilickap et al. [20] performed mathematical modelling and optimization of cutting force, tool wear and surface roughness by using the Artificial Neural Network and the Response Surface Methodology in milling of Ti6242S while Revankar et al. [21] analysed surface roughness and hardness in titanium alloy machining with polycrystalline diamond tool under different lubricating modes. The findings from these studies show that the cutting parameters and cutting conditions have a significant effect on the machinability of titanium alloy to the desired quality.

In an effort to enhance sustainability and machininability of titanium alloy, numerical methods for predicting temperature and surface hardness were reported [22]. This include developing a model for the optimizing energy consumption during the milling operation of titanium alloy (Ti6Al4V) [23]. Existing work has demonstrated the use of modelling and simulation tools such as Abaqus which were validated using physical experimentations to establish the optimum range of process parameter during the the milling operation of titanium alloy [24]. The modelling and optimization of the cutting parameters for the milling operation of titanium alloy has also been reported [25].

The machining parameters required for meeting the service and functional requirements of the titanium alloy (Ti6AIV) are still under investigation and have not been fully highlighted in literature. This paper aims to fill this gap by investigating the surface roughness during the milling operation of titanium alloy using the Response Surface Methodology (RSM). The succeeding sections present the materials and employed, results and discussion as well as conclusion and recommendations.

II. MATERIALS AND METHOD

The physical experiments were investigated using a DMU80monoBLOCK Deckel Maho 5-axis CNC milling machine and a mill cutter (SF550: HRC 40-HRC 50). A solid rectangular work piece of the titanium alloy (Ti6Al4V) was screwed to the stationary dynamometer (KISTLER 9257A 8-Channel Summation of Type 5001A Multichannel Amplifier) and mounted directly to the machine table. The Response Surface Methodology (RSM) was employed for the design of the numerical experiment with the range of the process parameters as follows: cutting speed (250-270 m/min), feed per tooth (0.05-0.30 mm) and axial depth of cut (0.50-3.0 mm). The choice of RSM was due to its ability to feasibly combine process parameters within the optimum range. The range of process parameters was determined based on previous studies [26-29]. These process parameters are varied over different levels while the surface roughness serves as the response of the designed experiment. The RSM produced 20 feasible combinations of the process parameters whose responses in terms of surface roughness (average surface roughness, Ra; average value of the maximum height of the profile, Rz; and average Root Mean Square (RMS) of surface profile Rg).

The numerical approach employed for this study is the Response Surface Methodology (RSM) and Central Composite Design (CCD). RSM and CCD have proven to be a suitable technique for the determination of most feasible combinations of process parameters and their cross effects on the response of the designed experiment [27].

Thus, the RSM with the Central Composite Design (CCD) were used to determine the feasible combination of process parameters for the milling operation. The general second-order polynomial RSM (full quadratic model) used for the experimental design is expressed as shown in (1) [30].

$$R_{u} = \beta_{0} + \sum_{i=1}^{n} \beta_{i} X_{iu} + \sum_{i=1}^{n} \beta_{ii} X_{iu}^{2} + \sum_{i$$

Where: *Ru* is the corresponding response and β_0 , β_1 , β_{ii} and β_{ij} represent the regression coefficients. The terms X_{iu} and X_{ju} are coded values of the ith and jth input parameters (*i*<*j*), while ε_u is the residual error.

The Design Expert software (version 11) was used for designing the RSM with CCD experiment. The summary of the experimentation design involving the three process parameters namely: cutting speed, feed per tooth and depth of cut is presented in Table I.

Notation	Independent Variables	Levels			
Touton		-1	0	1	
А	Cutting speed (m/min)	250	260	270	
В	Feed per tooth (mm)	0.50	0.40	0.30	
С	Depth of cut (mm)	0.50	1.75	3.00	

TABLE I. SUMMARY OF THE NUMERICAL EXPERIMENTATION

The machining data were collected with the aid of the stationary dynamometer (KISTLER 9257A 8-Channel Summation of Type 5001A Multichannel Amplifier) and the Data Acquisition System (DAQ) connected to the computer. The temperature during the cutting operation was measured with the aid of a professional infrared video thermometer with LCD display and camera function (MT 696) with infrared temperature range of -50-1000°C. The experimental set up is shown in Fig. 1.

During the cutting operation, cooling, was achieved with the aid of compressed air, which was supplied through the pipes and discharged from a nozzle to the interface of the cutting tool and work piece interface. The essence is to reduce the cutting temperature at the cutting tool and workpiece interface. This enables a comparative analysis between the magnitude of the surface roughness under the cooling and no cooling conditions.



Figure 1. The physical experimental set up [22].

A 3 flute 12 mm diameter mill cutter (Fig. 2) was employed during the milling operation and the specifications is shown in Table II.



Figure 2. The mill cutter.

TABLE II. THE CUTTING TOOL SPECIFICATIONS

Symbol	Parameter	Value
T _d	Tool diameter (mm)	12
F_l	Flute length (mm)	45
F _n	Number of flute	3
L	Overall length (mm)	100
β	Helix angle (deg.)	15
α1	Axial rake angle (deg.)	15
α2	Radial rake angle (deg.)	15

Equation 2 represents the average roughness (Ra) from measured profiles while (3-5) are formulas expressing the approximations of maximum height of profile (Rz) in milling operations.

Hence, the average surface roughness (Ra) and the peak to valley (Rz) for peripheral is expressed by (2-3) respectively.

$$R_{a} = \frac{1}{N} \sum_{i=0}^{N} y_{1}$$
 (2)

$$R_z = \frac{f_t^2}{8(\pm \frac{f_t \times N_t}{\pi})} \tag{3}$$

From Equation 3, conventionally the up milling takes the positive sign while the negative sign is used for the down milling.

For a circular path, (4) hold thus;

$$R_z = \frac{f_t (\cos\beta)^2}{8(R)} \tag{4}$$

For face milling operation, (5) is expressed as follows;

$$R_z = \frac{f_t}{tan\theta_c - cot\alpha} \tag{5}$$

Where: y_i is the ordinate of the profile, f_t is the feed per tooth (mm), N_t is the number of teeth, R is the radius of cutter (mm), θ_c is the corner angle (deg.), β is the helix angle (deg.) and α is the rake angle (deg.).

The Root Mean Square (RMS) which measures the deviation of the profile due to irregularities (Rq) is expressed as shown in (6).

$$R_q = \sqrt{\frac{1}{L} \int_0^l y^2 dx} \tag{6}$$

Where: *L* is the length of the surface measured (mm), *y* is the profile curve or irregularities while dx is the distance along L (mm).

The chemical composition, mechanical and thermal properties of the titanium alloy (Ti-6Al-4V) are presented in Tables III and IV respectively.

Element	Percent weight (wt. %)
Al	6
Fe	0.25
0	0.2
Ti	90
V	4

TABLE III. CHEMICAL COMPOSITION OF TITANIUM ALLOY (TI-6AL- 4V) [31]

TABLE IV. MECHANICAL AND THERMAL PROPERTIES OF TITANIUM ALLOY (TI-6AL-4V) [31]

S/N	Properties	Value
	Mechanical	
1.	Density (kg/m ³)	45000
2.	Brinell's hardness (BH)	334
3.	Yield strength (MPa)	880
4.	Ultimate tensile strength (MPa)	950
5.	Bulk modulus (GPa)	150
6.	Modulus of elasticity (GPa)	113.8
7.	Poison's ratio	0.342
8.	Shear modulus (GPa)	44
9.	Shear strength (MPa)	550
	Thermal	
1.	Specific heat capacity (J/g°C)	0.5263
2.	Thermal conductivity (W/m.K)	6.7
3.	Melting point (°C) 1660	
4.	Coefficient of thermal expansion (K^{-1})	8.70

Fig. 3 and 4 show the machined work piece and the Mitutoyo SJ - 201 surface roughness tester used for measuring the surface roughness. Three different types of surface roughness were determined namely: the average roughness (Ra), the maximum height of the profile (Rz) and the RMS of the surface roughness profile (Rq). The average roughness (Ra) is the roughness parameters which measures the deviation of a surface from its ideal form while the maximum height of the profile (Rz) is a measure of the maximum height of the profile. This is the difference between the largest five peaks and valleys within the sampling length. The surface roughness profile error (Rq) is a function of the Root Mean Square (RMS) of the profile irregularities. The measurements were replicated three times for each category of the surface roughness. The average value are computed as the magnitude of the average roughness presented in Table IV.



Figure 3. The machined titanium alloy work pieces.



Figure 4. The Mitutoyo SJ -201, surface roughness tester.

III. RESULTS AND DISCUSSION

The results obtained for the combination of the machining parameters and measured average roughness from the work piece after the cutting operation with and without intermittent cooling are presented in Tables 5 and 6. The machining operations were carried out with and without intermittent cooling in order to determine the effect of cooling on the surface roughness of the work piece.

Tables V and VI shows that the magnitude of the average roughness under air cooling and no cooling conditions. An increase in the magnitude of the cutting parameters (speed of cut, feed rate and depth of cut) beyond their optimum values resulted in increased surface roughness. The depth of cut is the perpendicular distance between the cut and uncut surfaces of the work piece, which is a measure of the thickness of the material removed during the machining operation. The higher the depth of cut beyond the optimum value, the lower the degree of the surface finish and vice versa. This is because the shear angle (angle of deformation) and the heat affected zone is a function of the depth of cut. Thus, an increase in the depth of cut beyond the optimum value (0.5 mm) increases the heat affected zone and the shear angle thereby producing a corresponding increase in the magnitude of the cutting force.

D					1 1 0	A D) (G	
Run	Cutting speed	Feed per tooth (mm)	Depth of cut (mm)	Average	Average value of	Average RMS	
	(m/min)			surface		of surface	
				roughness Ra	neight of the	profile Rq	
				(µm)	profile	(µm)	
					Rz (μm)		
1	260	0.30	1.80	0.400	2.02	0.523	
2	270	0.05	1.25	0.380	2.16	0.480	
3	260	0.15	1.50	0.466	2.26	0.590	
4	260	0.20	0.50	0.402	2.36	0.571	
5	275	0.20	2.00	0.400	2.22	0.546	
6	260	0.25	1.50	0.398	2.57	0.587	
7	250	0.07	2.50	0.393	2.55	0.493	
8	260	0.09	1.60	0.458	2.31	0.585	
9	265	0.10	1.50	0.436	2.61	0.539	
10	270	0.20	1.55	0.052	2.67	0.365	
11	275	0.07	0.55	0.060	2.17	0.406	
12	250	0.09	0.10	0.043	2.19	0.433	
13	260	0.20	0.65	0.040	2.12	0.453	
14	265	0.30	2.50	0.039	1.78	0.367	
15	270	0.05	2.40	0.046	1.45	0.366	
16	275	0.15	2.60	0.038	1.24	0.383	
17	265	0.20	2.4	0.035	1.12	0.277	
18	260	0.25	1.80	0.060	1.833	0.486	
19	270	0.08	1.75	0.046	1.75	0.457	
20	250	0.06	3.00	0.050	2.173	0.433	

TABLE V. THE CUTTING PARAMETERS AND THE SURFACE ROUGHNESS (AIR COOLING)

TABLE VI. THE CUTTING PARAMETERS AND THE SURFACE ROUGHNESS (NO COOLING)

Run	Cutting speed	Feed per tooth (mm)	Depth of cut (mm)	Average	Average value of the	Average	
	(m/min)			surface	maximum height of	surface	
				roughness	the profile	profile	Rq
				Ra (μm)	$\operatorname{Rz}(\mu m)$	(µm)	
1	260	0.30	1.80	0.578	2.896	0.602	
2	270	0.05	1.25	0.429	2.683	0.576	
3	260	0.15	1.50	0.685	2.750	0.640	
4	260	0.20	0.50	0.416	2.780	0.566	
5	275	0.20	2.00	0.687	2.670	0.654	
6	260	0.25	1.50	0.433	2.206	0.520	
7	250	0.07	2.50	0.588	2.476	0.587	
8	260	0.09	1.60	0.326	2.056	0.516	
9	265	0.10	1.50	0.782	2.894	0.673	
10	270	0.20	1.55	0.468	1.800	0.690	
11	275	0.07	0.55	0.689	2.764	0.763	
12	250	0.09	0.10	0.056	1.700	0.313	
13	260	0.20	0.65	0.064	2.468	0.458	
14	265	0.30	2.50	0.053	2.230	0.496	
15	270	0.05	2.40	0.068	2.576	0.557	
16	275	0.15	2.60	0.065	1.653	0.356	
17	265	0.20	2.4	0.056	1.926	0.446	
18	260	0.25	1.80	0.080	2.785	0.651	
19	270	0.08	1.75	0.070	2.087	0.346	
20	250	0.06	3.00	0.084	2.564	0.447	

Cutting force increases with an increase in the residual stress and cutting temperature. This tends to promote frictional activities and temperature increase as well as material's deposition on the rake face of the tool. This causes the development of built up edges with an increase in the surface roughness of the material [32].

Fig. 5 shows the effect of cooling and cutting speed on the average surface roughness during the cooling and noncooling cycles. The results obtained indicated that the average surface roughness reduces with intermittent aircooling. However, intermittent cooling causes an increase in the machining cycle time when compared to the noncooling cycles. The cutting speed measures the speed at which the tool approaches the work piece for material removal. From Fig. 5, an increase in the magnitude of cutting speed beyond the optimum results in an increased surface roughness for the cooling and non-cooling cycles. This is because an increase in the cutting speed increases the energy requirements of the process. Thus, bringing about heat generation at the work piece-tool interface. The generation of heat at the work piece-tool interface without cooling is detrimental to the cutting tool life and the surface finish of the work piece. It also makes the overall cutting process less sustainable in terms of energy consumption and environmental impact. Without cooling, residual stresses tends to build up within the work piece material, thus, resulting in an uneven surface.

Fig. 6 also shows the effect of cooling and cutting speed on the maximum height of the profile. The largest peaks for the heights and valley for 20 samples were measured during their cooling and non-cooling cycles. The results obtained indicate appreciable reduction in the magnitude of the surface roughness during the cooling cycle as compared with the non-cooling cycles. In addition, an increase in the magnitude of the cutting speed beyond the optimum value brings about an increase in the magnitude of the surface roughness.

Fig. 7 shows the Root Mean Square Error of the work piece profile with respect to the cutting speed. The deviation from the desired surface profile increases with an increase in the magnitude of the cutting feed during the cooling and non-cooling cycles. The deviation signals an increase in the magnitude of irregular surface profile which is more pronounced during the non-cooling cycles due to the build-up of residual stresses as a result of increase in temperature.

Fig. 8 shows the effect of feed rate on the average surface roughness during the cooling and non-cooling cycles. The feed rate measures the distance moved by the cutting tool in one revolution. When the feed rate increases beyond the optimum value (0.05 mm), the surface roughness increases and vice versa. This may be due to increasing temperature across the tool-chip interface which promotes the development of built up edges and chip fracture. Some feed marks were observed in the work piece, which indicates the presence of surface profiles which are not properly machined thereby increasing the surface roughness. The introduction of intermittent air cooling produced significant reduction in the magnitude of the surface roughness for the cooling cycles.

Fig. 9 shows the effect of cooling and feed rate on the maximum height of profile. The height of work piece profile irregularities increases with an increase in the magnitude of the feed rate beyond the optimum value. The irregularities were more pronounced during the cooling cycles when compared to the cooling cycles.

Fig. 10 shows the effect of cooling and feed rate on the Root Mean Square (RMS) of the surface profile. With an increasing magnitude of the feed rate beyond the optimum

without cooling, the RMS was pronounced which contributes to the increasing value of the surface roughness.

Fig. 11 and 12 show the surface roughness (average surface roughness, Ra; average value of the maximum height of the profile, Rz; and average surface profile Rq) under the air cooling and no cooling condition. For the cutting operation under both the air cooling and no cooling conditions, the results indicate that the magnitude of surface roughness decreases from the maximum height of the profile (Rz) to the average RMS of surface profile (Rq). The average surface roughness (Ra) has the least magnitude of roughness (Ra: 0.035 µm) for the cooling condition. The results also show that the magnitude of surface roughness was higher under the no cooling condition when compared to the air cooling condition for all the three types of surface roughness measured. This phenomenon can be traced to increased frictional activities especially in the shear zone during the cutting tool and work piece engagement in the absence of cooling. Abele and Frohlich [33] cite high thermal stress of titanium alloy due to its low thermal conductivity as one of the reasons for its poor surface finish during machining operations. The authors recommend the use of effective cooling strategy to minimise the thermal stress.

Furthermore, the milling operation is characterised by a cyclic nature of cutting force and chip formation mechanism. If the work piece is not adequately clamped the increasing temperature of the cutting tool can cause distortion. Distortion can also take place when the optimum cutting force is exceeded [34]. The cutting-tool and work piece distortion can increase the surface roughness due to vibration and cutting tool or work piece displacement. Ezugwu [35] explains that the low modulus of elasticity of titanium alloy is responsible for the material's deflection under high cutting force, thus causing springback. The selection of the cutting tool with coatings and right orientation, use of rigid machines with adequate clamping of the work piece, as well as the use of optimum cutting force are some of the ways to minimise vibration and chatter during the machining operation of titanium alloy [33, 35].







Figure 6. The effect of cooling and cutting speed on the maximum height of the profile.



Figure 7. The effect of cooling and cutting speed on the RMS of the surface profile.



Figure 8. The effect of cooling and feed rate on the average surface roughness.





Figure 9. The effect of cooling and feed rate on the maximum height of profile.



→ Air cooling — No cooling



Figure 10. The effect of cooling and feed rate on the RMS of the surface profile.

Figure 11. The average surface roughness (Air cooling).



Figure 12. The average surface roughness (No cooling).

IV. CONCLUSION

This study determines the effect of cooling conditions and milling parameters (cutting speed, feed rate and depth of cut on the surface roughness) on the surface roughness during the milling operation of Ti-6Al-4V The results obtained indicate that the optimum value of the process parameters which resulted in the least surface roughness (Ra:0.035 µm, Rz:1.12 µm and Rq 0.277 µm) under the air cooling condition were: cutting speed (265 m/min), feed per tooth (0.05 mm) and depth of cut (0.5 mm). An increase in the value of the speed of cutting, feed rate and depth of cut beyond this optimal values result in a corresponding increase in the magnitude of the surface roughness. A combination of an optimal values of the cutting speed and feed rates with low depth of cut produces better surface finish and thus recommended for this nature of machining operation. Furthermore, the results indicate that the magnitude of surface roughness decreases from the maximum height of the profile (Rz) to the average RMS of surface profile (Rq) while the average surface roughness (Ra) has the least magnitude of roughness under the cooling and no cooling conditions. In addition, the introduction of the air cooling condition reduces the magnitude of the surface roughness with reduction in feed marks and profile irregularities which increases the surface roughness. The study provides information on the combination of the most feasible cutting parameters and cutting conditions which promotes the surface quality of the titanium alloy (Ti-6Al-4V). Hence, the work finds application in the manufacturing industries, which employ the titanium alloy for product development. Future studies, can consider the development of mathematical models for the optimisation of the surface roughness of titanium alloy during milling operation. In addition, the effect of tool wear on the findings of this study can be investigated as part of future studies.

CONFLICT OF INTEREST

The authors declare no conflict of interest.

AUTHOR CONTRIBUTIONS

The work is a product of the collective efforts of all the authors.

ACKNOWLEDGMENT

The authors acknowledge the Institute of Advance Tooling, Soshanguve, South Africa.

Funding: The authors disclosed receipt of the following financial support for the research: Technology Innovation Agency (TIA) South Africa, Gibela Rail Transport Consortium (GRTC), National Research Foundation (NRF grant 123575) and the Tshwane University of Technology (TUT)."

REFERENCES

- B. Latha and V. S. Senthilkumar, "Modelling and analysis of surface roughness parameters in drilling GFRP composites using fuzzy logic," *Mater. Manuf. Process*, vol. 25, no. 8, pp. 817-827, 2010.
- [2] W. Habrat, M. Motyka, K. Topolski, and J. Sieniawski, "Evaluation of the cutting force components and the surface roughness in the milling process of micro- and nanocrystalline titanium," *Arch. Metall. Mater.*, vol. 61, no. 3, pp. 1379–1384, 2016.
- [3] E. Miko and L. Nowakowski, "Analysis and verification of surface roughness con- stitution model after machining process," *Procedia Eng.* vol. 39, pp. 395–404, 2012.
- [4] M. Tomov, M. Kuzinovski, and P. Cichosz, "A new parameter of statistic equality of sampling lengths in surface roughness measurement," Stroj Vestn–*Journal of Mechanical Eng.*, vol. 59 no. 5, pp. 339–48, 2013.
- [5] E. S. Gadelmawla, F. A. Al-Mufadi, and A. S. Al-Aboodi, "Calculation of the machining time of cutting tools from captured images of machined parts using image texture features," in *Proc IMechE Part B: J Engineering Manufacture*, vol. 228, no. 2, 203– 214, 2013.
- [6] A. S. Mohruni, M. Yanis, and E. Kurniawan, "Development of surface roughness prediction model for hard turning on AIAI D2 steel using cubic boron nitride insert," *Jurnal Teknologi (Sciences & Engineering)*, vol. 80, no. 1, pp. 173-178, 2018.
- [7] N. Qehaja, F. Zhujani, and F. Abdullahu, "Mathematical model determination for surface roughness during CNC end milling operation on 42CRM04 hardened steel," *International Journal of Mechanical Engineering and Technology*, vol. 9, no. 1, pp. 624– 632.
- [8] J. O. Osarenmwinda, "Empirical model for estimating the surface roughness of machined components under various cutting speed," *J. Appl. Sci. Environ. Management*, vol. 16, no. 1, pp. 65 – 68.

- [9] N. S. K. Reddy and P. V. Rao, "Selection of optimum tool geometry and cutting conditions using a surface roughness prediction model for end milling," *The International Journal of Advanced Manufacturing Technology*. vol. 26, no. (11-12), pp. 1202-1210, 2005.
- [10] Z. Hessainia, A. Belbah, M. A., Yallese, T. Mabrouki, and J. F. Rigal, "On the prediction of surface roughness in the hard turning based on cutting parameters and tool vibrations," *Measurement*. vol. 46, pp. 1671-1681, 2013.
- [11] I. Tlhabadira, I. A. Daniyan, L. Masu, and L. R. Van Staden, "Process design and optimization of surface roughness during M200 TS milling process using the Taguchi method," *Procedia CIRP* 84, pp. 868–873, 2019.
- [12] H. Aouici, M. A. Yallese, K. Chaoui, T. Mabrouki, and J. F. Rigal, "Analysis of surface roughness and cutting force components in hard turning with CBN Tool," *Measurement*. vol. 45, pp. 344-353, 2012.
- [13] A. Srithara, K. Palanikumar, and B. Durgaprasad, "Experimental investigation and surface roughness analysis on hard turning of AISI D2 steel using coated carbide insert," *Procedia Engineering*, vol. 97, pp. 72-77, 2014.
- [14] A. Agrawal, S. Goel, W. B. Rashid, and M. Price, "Prediction of surface roughness during hard turning of AISI 4340 steel (69 HRC)," *Applied Soft Computing*, vol. 30, pp. 279-286, 2015.
- [15] M. Tomov, M. Kuzinovski, and P. Cichosz, "Development of mathematical models for surface roughness parameter prediction in turning depending on the process condition," *International Journal* of Mechanical Sciences, vol. 113, pp. 120–132, 2016.
- [16] I. Tlhabadira, I. A. Daniyan, L. Masu, and K. Mpofu, "Computer aided modelling and experimental validation for effective milling operation of titanium alloy (Ti6AlV)," *Procedia CIRP*, vol. 91, pp. 113-120, 2020.
- [17] M. Mia, M. A. Khan, and N. R. Dhar, "Study of surface roughness and cutting forces using ANN, RSM, and ANOVA in turning of Ti-6Al-4V under cryogenic jet applied flank and rake faces of WC tool," *Int. J. Manuf. Technol.* vol. 93, pp. 975-991, 2017.
- [18] S. L. Ribeiro Filho, C. H. Lauro, L. C. Bueno, and L. C. Brandon, "Influence of cutting parameters on the surface quality and corrosion behaviour of Ti6Al4V in synthetic body environment (SBF) using Response Surface Method," *Measurement*, vol. 88, pp. 223-237, 2016.
- [19] G. A. Oosthuizen, K. Nnco, P. J. T. Conradie, and D. M. Dimitrov, "The effect of cutting parameters on surface integrity in milling Ti6Al4V," *South African Journal of Industrial Engineering*, vol. 27, no. 4, pp. 115-123, 2016.
- [20] E. Kilickap, A. Yardimenden, and Y. H. Celik, "Mathematical modelling and optimization of cutting force, tool wear and surface roughness by using artificial neural network and response surface methodology in milling of Ti6242S," *Applied Sciences*, vol. 7, no. 1064, pp. 1-12, 2017.
- [21] G. D. Revankar, R. Shetty, S. S. Rao, and V. N. Gaintode, "Analysis of surface roughness and hardness in titanium alloy machining with polycrystalline diamond tool under different lubricating modes," *Materials Research*, vol. 17, pp. 1010-1022, 2014.
- [22] I. A. Daniyan, I. Tlhabadira, K. Mpofu, and A. O. Adeodu. "Development of numerical models for the prediction of temperature and surface roughness during the machining operation of titanium alloy (Ti6Al14V)," *Acta Polytechnica Journal*, vol. 60, no. 5, 369–390, 2020.
- [23] I. Tlhabadira, I. A. Daniyan, L. Masu, and K. Mpofu, "Development of a model for the optimization of energy consumption during the milling operation of titanium alloy (Ti6Al4V)," *Materials Today: Proceedings*, vol. 38, pp. 614-620, 2021.
- [24] I. A. Daniyan, F. Fameso, F. Ale, K. Bello, and I. Tlhabadira, "Modelling, simulation and experimental validation of the milling operation of titanium alloy (Ti6Al4V)," *The International Journal* of Advanced Manufacturing Technology, vol. 109, no. 7, pp. 1853-1866, 2020.
- [25] I. A. Daniyan, I. Tlhabadira, S. N. Phokobye, S. Mrausi, K. Mpofu, and L. Masu, "Modelling and optimization of the cutting parameters for the milling operation of titanium alloy (Ti6Al4V)," in *Proc.* 2020 IEEE 11th International Conference on Mechanical and Intelligent Manufacturing Technologies (ICMIMT 2020). Added to IEEE Xplore, pp. 68-73, 2020.
- [26] I. A. Daniyan, K. Mpofu, and A. O. Adeodu, "Optimization of welding parameters using Taguchi and response surface

methodology for rail car bracket assembly," *The International Journal of Advanced Manufacturing Technology*. vol. 100, pp. 2221-2228, 2019.

- [27] I. A. Daniyan, I. Tlhabadira, S. N., Phokobye, M. Siviwe, and K. Mpofu. "Modelling and optimization of the cutting forces during Ti6Al4V milling process using the response surface methodology and dynamometer," *MM Science Journal*, vol. 128, pp. 3353-3363, 2019.
- [28] I. A. Daniyan, I. Tlhabadira, O. O. Daramola, S. N. Phokobye, M. Siviwe, and K. Mpofu, "Measurement and optimization of cutting forces during MS 200TS milling process using the response surface methodology and dynamometer," *Procedia CIRP*, vol. 88, pp. 288-293, 2020.
- [29] O. O. Daramola, I. Tlhabadira, J. L. OlajideI, A. Daniyan, E. R. Sadiku, and L. Masu, "Process design for optimal minimization of resultant cutting force during the machining of ti-6al-4v: response surface method and desirability function analysis," *Procedia CIRP*, vol. 84, pp. 854–860, 2019.
- [30] S. M. Baligidad, U. Chandrasekhar, K. Elangovan, and S. Shankar, "RSM optimization of parameters influencing mechanical properties in selective inhibition sintering," *Materials Today: Proceedings*, vol. 5, no. 2, pp. 4903-4910, 2018.
- [31] U.S. Titanium Industry Inc... Titanium Alloys Ti6Al4V Grade 5. AzoM, 2017. [Online] Available at https://www.azom.com/properties.aspx?ArticleID=1547 [Accessed July 02, 2019].
- [32] K. C. Anil, M. G. Vikas, T. B. Shanmukha, and R. Sreenivas, "Effect of cutting parameters on surface finish and machinability of graphite reinforced Al-8011 matrix composite," *IOP Conf. Series: Materials Science and Engineering*, vol. 191:012025, pp. 1-6, 2017.
- [33] E. Abele and B. Frohlich, "High speed milling of Ti-alloys," Advances in Production Engineering & Management, vol. 3, pp. 131-140, 2008.
- [34] I. Tlhabadira, I. A, Daniyn, R. Machaka, C. Machio, L. Masu, and L. R. VanStaden, "Modelling and optimization of surface roughness during AISI P20 milling process using Taguchi method," *Int'l Journal of Adv. Manuf. Technol.* vol. 102, pp. 3707-3718, 2019.
- [35] E. O. Ezugwu and Z. M. Wang. "Titanium alloys and their machinability – a review," *Journal of Materials Processing Technology*, vol. 68, pp. 262-274, 1997.

Copyright © 2021 by the authors. This is an open access article distributed under the Creative Commons Attribution License (<u>CC BY-NC-ND 4.0</u>), which permits use, distribution and reproduction in any medium, provided that the article is properly cited, the use is non-commercial and no modifications or adaptations are made.



Ilesanmi Afolabi Daniyan is a Postdoctoral Research Fellow at the Department of Industrial Engineering, Tshwane University of Technology, Pretoria, South Africa. His research interest include Production Engineering and Advanced Manufacturing.



Isaac Tlhabadira is the Director, Technology and Innovation, Tshwane University of Technology, Pretoria, South Africa. His research interest is in the field of manufacturing technology



Khumbulani Mpofu is the Research Chair in Manufacturing and Skills Development, Department of Industrial Engineering, Tshwane University of Technology, Pretoria, South Africa. His research interest is in the field of include advanced manufacturing



Rumidzai Muvunzi is a Postdoctoral Research Fellow at the Department of Industrial Engineering, Tshwane University of Technology, Pretoria, South Africa. Her research include advanced and additive manufacturing.